



Sodium Metaborate 4 Mol

Product Profile

NaBO₂·2H₂O [or Na₂B₂O₄·4H₂O]
Sodium Metaborate Dihydrate
Technical Grade – Granular
CAS Number 16800-11-6

Sodium metaborate 4 mol, an alkaline salt with excellent buffering properties, consists of white crystalline granules. The high solubility of sodium metaborate 4 mol can provide a much higher concentration of borate ions in solution than Neobor® borax 5 mol or borax at the same temperature.

Applications and Benefits

Photochemicals

Sodium metaborate 4 mol is used as a component of photographic developers and replenishers. Its principal function as a buffering agent is to control the pH within close limits. This is essential both in fine grain black-and-white developers and in ensuring the correct color balance in color developers.

Adhesives

The specific effect of sodium metaborate 4 mol in the preparation of starch and dextrin adhesives is due to the high degree of alkalinity and the crosslinking reaction of borate anions with polyhydroxy groups. The interchain linkage produces an adhesive with increased viscosity, quicker tack and better fluidity properties. These qualities are essential for use in corrugated boxes, paper bags, laminated paper boards, carton/case sealing, gummed tape, and tube winding.

Textile processing

Textiles such as cotton are bleached with hydrogen peroxide solutions which can be stabilized by sodium metaborate. In addition, sodium metaborate neutralizes the acidic oxidation products formed during bleaching.

Textile sizing can be controlled by incorporation of the adhesive material within the thread and by binding all the fibers together to increase the tensile strength of the thread. Sodium metaborate is added to the starch adhesives to accomplish these functions.

Detergents and cleaners

Sodium metaborate 4 mol is used in hard surface cleaners to remove oil, grease, rust, scale and other particulates from metal or glass surfaces. The cleaning action is enhanced by the alkaline conditions imparted by sodium metaborate. Sodium metaborate can also be incorporated in liquid laundry detergents for pH control, enzyme stabilization, and its builder properties.

Corrosion inhibition

Sodium metaborate 4 mol is incorporated in many proprietary water treatment chemicals requiring pH control and corrosion inhibition. They are used for protecting central heating systems and cooling towers against corrosion.

Chemical and Physical Properties

Theoretical composition

Boric oxide, B ₂ O ₃	34.19%
Sodium oxide, Na ₂ O	30.43%
Water of crystallization, H ₂ O	35.28%
Anhydrous equivalent, NaBO ₂	64.62%

Characteristics

Molecular weight, NaBO ₂ ·4H ₂ O	101.83
Specific gravity	1.90

Stability

Sodium metaborate 4 mol is stable at ordinary temperatures. If exposed to the atmosphere for extended periods, it will pick up carbon dioxide from the air and form sodium carbonate and borax. Sodium metaborate 4 mol shows little tendency to cake except after prolonged storage or if it becomes severely wetted by rain or substantial water penetration. When stored



Sodium Metaborate 4 mol Product Profile

under normal conditions of temperature and humidity, sodium metaborate 4 mol is unlikely to cake or change chemically.

Melting point

The crystalline salt begins to melt in its own water at about 90°C (194°F). The anhydrous salt fuses to a clear glass at 966°C (1770°F). Some vaporization occurs above 1230°C (2246°F).

Hydrogen ion concentration

Aqueous solutions of sodium metaborate 4 mol show a moderate increase in pH with increasing concentration:

Sod. met. 4 mol (wt.)	pH @ 20°C (68°F)
0.1%	10.6
0.5%	10.9
1.0%	11.1
2.0%	11.3
4.0%	11.5
6.0%	11.6
8.0%	11.8
10.0%	11.8
15.0%	12.0
18.0%	12.2

Solubility in water, as NaBO₂·4H₂O [or Na₂B₂O₄·8H₂O]

Temp °C (°F)	% by weight
0 (32)	22.4
5 (41)	24.3
10 (50)	26.3
15 (59)	28.6
20 (68)	31.0
25 (77)	33.4
30 (86)	36.5
35 (95)	39.6
40 (104)	43.2
45 (113)	47.7
50 (122)	52.8
53.6* (128.6)	57.1
55 (131)	57.6
60 (140)	59.3
65 (149)	61.1
70 (158)	63.3
75 (167)	65.3
80 (176)	67.6
85 (185)	70.3
90 (194)	73.4
95 (203)	76.8
100 (212)	81.1

*Exists as sodium metaborate 8 mol below 53.6°C; transition to sodium metaborate 4 mol, which is stable, from 53.6°C to 105°C.

Notice:

Before using these products, please read the Product Specifications, the Safety Data Sheets and any other applicable product literature.

The descriptions of potential uses for these products are provided only by way of example. The products are not intended or recommended for any unlawful or prohibited use including, without limitation, any use that would constitute infringement of any applicable patents. Nor is it intended or recommended that the products be used for any described purposes without verification by the user of the products' safety and efficacy for such purposes, as well as ensuring compliance with all applicable

laws, regulations and registration requirements. Suggestions for use of these products are based on data believed to be reliable. The seller shall have no liability resulting from misuse of the products and provides no guarantee, whether expressed or implied, as to the results obtained if the products are not used in accordance with directions or safe practices. The buyer assumes all responsibility, including any injury or damage, resulting from misuse of the product, whether used alone or in combination with other materials. THE SELLER MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THE SELLER SHALL HAVE NO LIABILITY FOR CONSEQUENTIAL DAMAGES.

A member of the Rio Tinto Group

Borax Asia Pte. Ltd.
501 Orchard Road
#08-02 Wheelock Place
Singapore 238880
Tel: (65) 738 6068
Fax: (65) 738 6282

Borax Europe Limited
1A Guildford Business Park
Guildford, GU2 8XG
United Kingdom
Tel: (44) 1483 242000
Fax: (44) 1483 242001

U.S. Borax Inc.
26877 Tourney Road
Valencia, California, 91355-1847
United States
Tel: (1) 661 287 5400
Fax: (1) 661 287 5495

www.borax.com